

PRODUCT CATALOG – TRIPLEX SERVICE DROP

Code Name	Phase Conductors		Insul Thick. (mils)	Bare Neutral Messenger		Rated Strength (Lbs)	Lbs/1000 Ft.	
	Size AWG or MCM	Size		Size A	WG or MCM**		Cross linked Polyeth	Polyeth
With 6201 Alloy Neutral Messenger								
Minex	6	Solid	45	6	7/w	1,110	106.6	102.9
Hippa	6	7/w	45	6	7/w	1,110	113.2	105.7
Prawn	4	Solid	45	4	7/w	1,760	158.4	154.1
Barnacles	4	7/w	45	4	7/w	1,760	168.3	158.2
Shrimp	2	7/w	45	2	7/w	2,800	253.7	239.7
Gammarus	1/0	7/w	60	1/0	7/w	4,460	411.6	390.6
Leda	1/0	19/w	60	1/0	7/w	4,460	402.7	386.0
Dungeness	2/0	7/w	60	2/0	7/w	5,390	506.8	482.7
Cyclops	2/0	19/w	60	2/0	7/w	5,390	495.3	476.3
Flustra	3/0	19/w	60	3/0	7/w	6,790	611.4	589.1
Lepas	4/0	19/w	60	4/0	7/w	8,560	757.1	730.5
With 6201 Alloy Reduced Neutral Messenger								
Arternia	4	Solid	45	6	7/w	1,110	141.4	137.1
Crab	4	7/w	45	6	7/w	1,110	151.3	141.2
Solaster	2	7/w	45	4	7/w	1,760	226.6	212.6
Sandcrab	1/0	7/w	60	2	7/w	2,800	368.8	347.8
Echinus	1/0	19/w	60	2	7/w	2,800	358.8	343.1
With AAC Neutral Messenger								
Haiotis	6	Solid	45	6	7/w	563	102.5	98.8
Patella	6	7/w	45	6	7/w	563	109.1	101.6
Fusus	4	Solid	45	4	7/w	881	151.9	147.6
Oyster	4	7/w	45	4	7/w	881	161.8	151.7
Clam	2	7/w	45	2	7/w	1,350	243.2	229.2
Murex	1/0	7/w	60	1/0	7/w	1,990	395.1	373.0
Purpura	1/0	19/w	60	1/0	7/w	1,990	386.1	369.4
Nassa.	2/0	7/w	60	2/0	7/w	2,510	485.8	460.7
Trophon	2/0	19/w	60	2/0	7/w	2,510	474.3	455.3
Melita	3/0	19/w	60	3/0	19/w	3,310	585.2	562.9
Portunas	4/0	19/w	60	4/0	19/w	4,020	723.9	697.3
Nannynose	4/0	19/w	80	4/0	19/w	6,150	1160.4	1118.0

** Designated sizes are ASCR 611 diameter equivalent and AAC with equivalent resistivity per ASTM B-399 for 6201. The code names as given apply to conventional polyethylene line wire. For cross-linked polyethylene, the suffix XLP should be added such as "Hombeam -XLP" Standards: ASTM B-230, B-231, B-232 and B-399, ICEA S-61-402 and S-66-524.

REA Approved. Packaging: Available in 500 ft. coils for sizes 2 A WG and smaller and in long lengths on reels.

The above data are approximate and subject to normal manufacturing tolerances.